

Facestock

A white matt polyethylene film with a with a toner-receptive surface.

Basis Weight	115 g/m ²	ISO 536
Caliper	178 µm	ISO 534

Adhesive

AL171 is a transparent, solvent-based permanent, acrylic adhesive

Liner

BG40 white, a supercalendered glassine paper.

Basis Weight	59 g/m ²	ISO 536
Caliper	53 µm	ISO 534

Laminate

Total Caliper	263 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	13 N/25mm	FTM 9 Glass
Peel Adhesion 90°	7 N/25mm	FTM 2 St.St.
Min. Application Temp.	10 °C	
Service Temperature	-80 °C to 140 °C	

Adhesive Performance

AL 171 is an adhesive of extremely high ageing stability for long-term applications.

Applications and Use

By virtue of its very good toner keying properties and its high scratch and abrasion resistance, facematerial is ideal, for example, for transport and warehousing applications, and also for product and component identification in industry. Tests prior to use are recommended to ensure that the product works under your application conditions.

Conversion and Printing

The facematerial allows printing by conventional printing techniques including flexo, screen, offset, letterpress and gravure. For flexo good results can be achieved with water- or solvent-based printing inks. Consult your printing ink supplier about suitable printing inks for your application.

Compliance and Approvals

The adhesive has been tested in accordance with DIN ISO 3826. It complies with FDA 175.105 for indirect contact with foodstuff. AL171 also meets the requirements of the so-called "Toy Standard" EN 71-3.


Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AA134

Fasson ®

PE105 MATT WHITE AL171-BG40WH



PE105 MATT WHITE

AL171

BG40WH

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended. If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2021 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.