

Facestock

White, uncoated, both sides matt finished HDPE film. Ideal where high tear strength is required.

| | | |
|---------------------|-----------------------|-----------|
| Basis Weight | 130 g/m ² | ISO 536 |
| Caliper | 145 µm | ISO 534 |
| Elongation CD | <230 % | DIN 53455 |
| Elongation MD | <200 % | DIN 53455 |
| Opacity | 90 % | DIN 53146 |
| Whiteness | 90 % | ISO 2470 |
| Tensile strength MD | >55 N/mm ² | DIN 53455 |
| Tensile strength CD | >43 N/mm ² | DIN 53455 |

Applications and Use

This product is ideal for applications where durability, strength, moisture, grease and chemical resistance are required.

Conversion and Printing

Good printability with flexo, gravure, letterpress, screen, offset and thermal transfer printing techniques. Excellent converting properties eg. guillotining, slitting, die cutting and hole punching.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AD194

Fasson ®

POLYART HS 130



POLYART HS 130

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2022 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.