

#### Facestock

A gloss white polyester film. The smooth surface is print treated to achieve good TT printability and ink anchorage.

Basis Weight	71 g/m <sup>2</sup>	ISO 536
Caliper	50 µm	ISO 534

#### Adhesive

S8030 is a high strength permanent solvent based acrylic adhesive.

#### Liner

BG42 white, a supercalendered glassine paper.

Basis Weight	65 g/m <sup>2</sup>	ISO 536
Caliper	58 µm	ISO 534
Transparency	50 %	DIN 53147

#### Laminate

Total Caliper	132 µm±10%	ISO 534
---------------	------------	---------

#### Performance Data

Initial Tack	16 N/25mm	FTM 9 Glass
Peel Adhesion 90°	12 N/25mm	FTM2 st.st.
Min. Application Temp.	7 °C	
Service Temperature	-40 °C to 150 °C	
Adhesive Coat Weight	24 g/m <sup>2</sup>	FTM12
Adhesive Type	Solvent Acrylic	

#### Adhesive Performance

S8030 features a balanced adhesive performance on a wide variety of substrates including low energy plastics combined with good chemical resistance.

#### Applications and Use

Transfer PET White PT is specifically developed for Durable Goods labelling. Typical examples are identification and warning labels on electronic devices and household appliances.

This all-round performing product provides good adhesion onto low surface energy plastics combined with the long term durability expected from a solvent acrylic adhesive.

#### Conversion and Printing

The glossy, smooth surface is print treated and can be thermal transfer printed, the best results can be obtained with resin ribbons. This product is qualified by EFI Jetrion and Durst for UV inkjet printing. It can be printed by all conventional print technologies.

#### Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

## AD225

### Fasson®

#### TRANSFER PET WHITE PT S8030-BG42WH



TRANSFER PETWH PT

S8030

BG42WH

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

## Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000



### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2021 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.