

Facestock

A gloss white polyester film. The smooth surface is covered with a topcoat for very good ink anchorage.

| | | |
|--------------|---------------------|---------|
| Basis Weight | 76 g/m ² | ISO 536 |
| Caliper | 50 µm | ISO 534 |

Adhesive

S8049 is a rubber hybridised acrylic (RHA) adhesive.

Liner

BG42Wh BSS: on both sides siliconized glassine paper, woodfree, super calandered and extremely tough and tear-resistant despite its thinness.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

| | | |
|--------------|---------------------|---------|
| Basis Weight | 64 g/m ² | ISO 536 |
| Caliper | 55 µm | ISO 534 |

Laminate

| | | |
|---------------|------------|---------|
| Total Caliper | 150 µm±10% | ISO 534 |
|---------------|------------|---------|

Performance Data

| | | |
|-------------------|-----------|----------------------|
| Initial Tack | 25 N/25mm | FTM 9 Glass |
| Peel Adhesion 90° | 25 N/25mm | FTM 2 st.st. 24hr |

| | |
|------------------------|------------------|
| Min. Application Temp. | 5 °C |
| Service Temperature | -40 °C to 150 °C |

| | | |
|----------------------|---------------------------------|-------|
| Adhesive Coat Weight | 45 g/m ² | FTM12 |
| Adhesive Type | rubber hybridised acrylic | |

Adhesive Performance

S8049 combines extremely high peel adhesion, also on low surface energy substrates, with excellent chemical, UV and temperature resistance.

Applications and Use

Transfer PET white TOP is designed for conversion into identification, warning and tracking labels for durable goods such as automotive parts, electronic devices and home appliances. This product is distinguished by the high chemical resistance of the thermal transfer print. For special requirements we strongly recommend application tests.

This is a premium product for the automotive industry using Avery Dennison RHA (rubber hybridised acrylic) adhesive technology. It is designed primarily for creating labels to be applied onto low surface energy plastic automotive parts and lacquers or other rough or low surface energy surfaces. S8049 products are engineered to be resistant to - also harsh - chemicals commonly found in the automotive and electronics industry.

Because of the high coat weight and high tack of the adhesive, there is a risk of adhesive ooze. Special care has to be taken in the conversion process. It is recommended to contact the supplier of die cutting equipment to specify the most suitable tool. Good results have been achieved using a 60° cutting angle with laser hardening and a no-stick coating.

AJ059

Fasson®

TRANSFER PET WHITE TOP S8049-BG42WH BSS FSC



TRANSFER PET WHITE TOP

S8049

BG42WH BSS FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Conversion and Printing

Very good results can be achieved with thermal transfer printers equipped with conventional or near-edge print heads using resin ribbons. Transfer PET white TOP can also be printed by all conventional roll label techniques, including flexo, UV letterpress, silkscreen. This material is qualified for UV inkjet printing by the following printer manufacturers: EFI Jetrion, Domino (n610i), Durst (TAU 330 RSC) and Xeikon (PX3000). Results of durability tests are available on request. For easy diecutting sharp corners should be avoided.

Compliance and Approvals

Sustainable alternative: This material is available with 70% recycled content in the face material under a *different product code*.

This product is UL and C-UL recognized (UL 969, CSA C22.2 No. 0.15). The UL file number is MH27538.

Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Appendix

UL and CSA recognition

This product meets the requirements as stated in UL 969 and CSA C22.2 No. 0.15 for indoor and outdoor use. The UL file number is MH27538. For specific information on approved conditions, see appendix.

Performance Data

Note: the following technical data should be considered representative or typical only and should not be used for specification purposes.

Peel Adhesion:

FTM1: 180°, 300 mm/min, dwell time: 48 hours

| Surface | N/25mm |
|----------------------------------|--------|
| ABS | 35,0 |
| Aluminium | 35,5 |
| Automotive lacquered panels | 35,0 |
| Glass | 37,0 |
| HDPE | 32,0 |
| LDPE | 31,0 |
| PA6 | 36,0 |
| Polycarbonate (PC) | 37,0 |
| Polyethylenetherephthalate (PET) | 37,5 |
| Polypropylene (PP) | 34,0 |
| Polystyrene (PS) | 31,0 |
| Stainless Steel | 37,0 |

Due to the unique RHA technology we strongly recommend waiting for 24 hours after application before performing any adhesive testing.

Chemical Resistance:

The performance results are based on 4 hours immersions at room temperature unless otherwise noted. Samples were applied to the test panel and conditioned for 24 hours before immersion and evaluated immediately upon removal. Peel adhesion was measured according to FTM1.

| Chemical | Test Substrate | N/25mm | Visual appearance | Edge Penetration |
|-------------------|-----------------|--------|-------------------|------------------|
| Ad Blue | Stainless Steel | 28,0 | No change | 0 mm |
| Biodiesel | Stainless Steel | 35,0 | No change | 0 mm |
| Bioethanol E85 | Glass | 29,0 | No change | 2 mm |
| Brake Fluid | Glass | 35,7 | No change | 0 mm |
| Diesel | Glass | 34,5 | No change | 0,5 mm |
| Engine Oil | Glass | 36,5 | No change | 0 mm |
| Gasoline | Glass | 22,7 | No change | 4,5 mm |
| Heptane | Glass | 23,5 | No change | 5 mm |
| Water, distilled | Aluminum | 29,5 | No change | 0 mm |
| Windshield washer | Stainless Steel | 31,5 | No change | 0 mm |

Chemicals: Ad Blue: Aral, Bioethanol E85: CropEnergies CropPower85, Brake Fluid: DOT 4 Synthetic (One Way)
Diesel: TOTAL, Engine Oil: TOTAL quartz 700, 10 W 40, Gasoline: TOTAL Euro 95

Appendix

Thermal Transfer Printing:

Printability – Physical Resistance

Flat head printers (tests were performed with the printer Zebra XII 140):

| Ribbon | Settings speed energy | | Print Quality | ANSI Grade | Scratch resistance | Tape resistance |
|--------------|--------------------------|----|---------------|------------|-----------------------|--------------------|
| Armor AXR7+ | 3 | 20 | ++ | A | ++ | ++ |
| Armor AXR8 | 3 | 15 | ++ | A | ++ | ++ |
| DNP R300 | 3 | 15 | ++ | A | ++ | ++ |
| DNP R510 | 3 | 20 | ++ | A | ++ | ++ |
| limak SP330 | 3 | 15 | ++ | A | ++ | ++ |
| ITW B324 | 3 | 15 | ++ | A | ++ | ++ |
| Ricoh B110CR | 3 | 15 | ++ | A | ++ | ++ |
| Zebra 4800 | 3 | 20 | ++ | A | ++ | ++ |
| Zebra 5095 | 3 | 15 | ++ | A | ++ | ++ |

Near edge printers (tests were performed with the printer Avery TTX 450 – Near Edge):

| Ribbon | Settings | Print Quality | ANSI Grade | Scratch resistance | Tape resistance |
|---------------|----------|---------------|------------|-----------------------|--------------------|
| Armor AXR 600 | 4 "/s | + | A | ++ | o |
| Armor AXR 800 | 4 "/s | + | B | ++ | o |
| Ricoh B120 E | 4 "/s | ++ | A | + | + |

ANSI (American National Standards Institute) Grade: information about barcode quality

A: excellent B: good C: acceptable D: readable with difficulty

++: excellent +: good o: acceptable -: poor

Chemical Resistance

The printed samples were wetted on the surface with a soft clean cotton cloth soaked in the test solution by wiping 10 times back and forth with light pressure. After 5 seconds they were dried with a clean dry soft cloth. After 15 minutes the evaluation took place.

| | AXR7+ | AXR8 | R300 | R510 | SP330 | B324 | B110 CR | Z-4800 | Z-5095 | AXR 600 | AXR 800 | B120 E |
|-----------------|-------|------|------|------|-------|------|------------|--------|--------|---------|---------|--------|
| Ad Blue | + | + | + | + | + | + | + | + | + | + | + | + |
| Anti-Freeze | + | + | + | + | + | + | + | + | + | + | + | + |
| Biodiesel | + | o | + | + | + | + | + | + | + | - | o | - |
| Bioethanol E85 | - | + | + | + | + | + | + | - | + | - | o | - |
| Brake fluid | - | + | + | + | o | + | + | - | o | - | o | - |
| Cleaner solvent | + | + | + | + | + | + | + | + | + | - | - | - |
| Engine oil | + | + | + | + | + | + | + | + | + | + | + | o |
| Gasoline | - | o | - | + | - | - | - | - | - | - | - | - |
| Hard wax polish | + | + | + | + | + | + | + | + | + | - | - | - |
| Isopropanol | + | + | + | + | + | + | + | + | + | - | o | - |
| Spirit | - | + | + | + | + | + | + | - | + | - | o | - |

+: good (no change) o: acceptable (minor change, still readable) -: poor

Chemicals:

Ad Blue: Aral, Anti-Freeze: Speedfrost "Speedfroil" 1:1 in water, Bioethanol E85: CropEnergies CropPower85

Brake Fluid: DOT 4 Synthetic (One Way), Cleaner Solvent: "Caramba" Cold Cleaner, Engine Oil: TOTAL quartz 700, 10 W 40

Gasoline: TOTAL Euro 95, Hard Wax Polish: „Nigrin“ Hard Wax Polish

Appendix

Compliance Data

UL – Underwriters Laboratories (UL 969, Category PGJ12)

File Number: MH27538, Category PGJ12

This material is UL recognized for indoor and outdoor use where exposed to high humidity or occasional exposure to water.

| Application Surface | Max Temp (°C) | Min Temp (°C) | I | O |
|-----------------------------------|---------------|---------------|---|---|
| Acrylic paint | 150 | -40 | X | X |
| Acrylic powder paint | 150 | -40 | X | X |
| Alkyd paint | 150 | -40 | X | X |
| Aluminum | 150 | -40 | X | X |
| Chromate treated metal | 150 | -40 | X | X |
| Epoxy paint | 150 | -40 | X | X |
| Epoxy powder paint | 150 | -40 | X | X |
| Galvanised steel | 150 | -40 | X | X |
| Polyester paint | 150 | -40 | X | X |
| Polyester powder paint | 150 | -40 | X | X |
| Polyurethane powder paint | 150 | -40 | X | X |
| Stainless steel | 150 | -40 | X | X |
| Unsaturated polyester – thermoset | 150 | -40 | X | X |
| Nylon – Polyamide | 100 | -40 | X | X |
| Phenolic – Phenol Formaldehyde | 100 | -40 | X | X |
| ABS | 80 | -40 | X | X |
| Polyphenylene oxide/ether (PPOX) | 80 | -40 | X | - |
| Polypropylene | 80 | -40 | X | X |
| Polystyrene (PS) | 80 | -40 | X | X |
| Polycarbonate | 60 | -40 | X | X |
| Polyethylene | 60 | -23 | X | X |

I: Indoor use O: outdoor use

The UL certification includes the printing with EFI Jetrion, “Jetrion 4000”, Durst “Tau 330 RSC”, Xeikon “PantherCure UV”, Domino “N610i” and the following thermal transfer ribbons:

| | |
|---------------------------|---|
| Armor | AXR 600, AXR 7+, AXR 8 |
| Astro-med | R-5, RAF, RF, RY |
| Coding Products | 5440 (Red), 5640 (Blue), 5940 |
| Dainippon | R300, R510, R510 (Blue), R510 (Green), R510 (Red, indoor use only), R550, Signature Series (TM) Resin, TR4070, TR6070, TR6075 |
| Dasco | DR 74, DR 84 |
| Datamax | PGR, SDR, SDR Millennium, SDR-4, SDR-5, SDR-6, SDR-7, SDR-A, SDR-D |
| ITW | B324, M 95, R90, R91 |
| limak | Primemark, Primemark 255, SH-36, SP-330, SP-410, SP-575 |
| Intermec Corp. | 053258-2, 054048-4, TMX1500, TMX3200 |
| Japan Pulp and Paper | Resin 1, Resin 2 (Blue), Resin 2 (Green), Resin 2 (Red, indoor use only), Sigma P |
| Kurz | K300, K500, K501 |
| Mid-City Columbia Inc. | CGL 80HE, MCC-23HE |
| Monarch | 9446 |
| NCR | K3, Matrix Resin, PaceSetter, Perma Max, Promark III, Ultra V |
| Peak | Ultra Extreme, Ultra Premium |
| RSI ID Technologies | Pressiza H, Pressiza K, Pressiza R, Pressiza S, Pressiza X |
| Ricoh | 120 EC, B110C, B110CR, B110CX |
| Sato Corp. | Premier 1 |
| Sony Chemicals | 4072, 4075, 4080, 4085, 4571, 5070, TRX-75 |
| Union Chemcar Am. | US300 |
| United Barcode Industries | HR06 |
| Zebra Technologies | 5095, 5100, 5175, 5463, 5555, Z-1400, Z-3100, Z-4100 |

Appendix

CSA – Canadian Standards Association

UL has tested this product according to the requirements described in CSA C22.2 No. 0.15.

This product is C-UL recognized for indoor and outdoor use.

The details are listed in the UL file number MH27538, Category PGJ18.

| Group | Application Surface | Max. Temperature (°C) |
|-----------------------------|---|-----------------------|
| Metals | Bare, plated or enamelled steel; bare, anodized or enamelled aluminium | +150 |
| Powder coated metal Group C | Epoxy powder coat paint | +150 |
| Powder coated metal Group D | Polyurethane powder coat paint | +150 |
| Plastic Group I | Phenolic, melamines, urea formaldehyde | +100 |
| Plastic Group II | Polyphenylene oxide, polyphenylene sulphide | +80 |
| Plastic Group III | Polycarbonate, acetates, acrylics | +80 |
| Plastic Group IV | Polyethylene, polypropylene, polybutylene | +80 |
| Plastic Group V | Polyamide, polyimide | +80 |
| Plastic Group VII | PVC (rigid), PVC plasticized | +80 |
| Plastic Group VIII | Glass-filled polyester, glass-filled epoxy | +80 |

The C-UL certification includes the printing with EFI Jetrion, "Jetrion 4000", Durst "Tau 330 RSC", Xeikon "PantherCure UV", Domino "N610i" and the following thermal transfer ribbons:

| | |
|------------------------|--|
| Armor | AXR 600, AXR 7+, AXR 8 |
| Astro-med | RAF, RF, RY |
| Coding Products | 5440 (Red), 5640 (Blue) |
| Dainippon | R300, R510, R510 (Blue), R510 (Green), R510 (Red, indoor use only), Signature Series (TM) Resin, TR4070, TR6070, TR6075 |
| Datamax | SDR, SDR Millennium, SDR-5, SDR-6, SDR-7, SDR-A, SDR-D |
| ITW | B324, R90 |
| Iimak | SP-575 |
| Intermec Corp. | 053258-2, 054048-4 |
| Japan Pulp and Paper | Resin 1 |
| Kurz | K500 |
| Mid-City Columbia Inc. | CGL 80HE, MCC-23HE |
| NCR | Matrix Resin, Promark III |
| Peak | Ultra Extreme, Ultra Premium |
| RSI ID Technologies | Pressiza K, Pressiza S, Pressiza X |
| Ricoh | B110C, B110CR |
| Sato Corp. | Premier 1 |
| Sony Chemicals | 5070, TRX-75 |
| Union Chemicar | US300 |
| America | |
| Zebra Technologies | 5100 |

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2024 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.