

Facestock

A clear bi-axially oriented, polypropylene film with a print-receptive topcoat.

Basis Weight	44 g/m ²	ISO 536
Caliper	48 µm	ISO 534

Adhesive

A clear, general purpose permanent, acrylic adhesive.

Liner

A clear polyester liner giving optimum smoothness to the adhesive layer. rPET23 liner contains up to 30% recycled Post-Consumer Recycled (PCR) content. This liner is 100% recyclable. Visit our website for more information.

Basis Weight	32 g/m ²	ISO 536
Caliper	23 µm	ISO 534

Laminate

Total Caliper	87 µm±10%	ISO 534
---------------	-----------	---------

Performance Data

Initial Tack	9 N/25mm	FTM 9 Glass
Peel Adhesion 90°	5.5 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-40 °C to 80 °C	

Adhesive Performance

S7000 exhibits a balance of release properties to enable high speed converting and dispensing on increasingly thinner substrates. Designed for application on dry surfaces. Excellent wet out characteristics and water-whitening resistance. Significantly less adhesive bleed vs. Industry standard, which reduces downtime on press and dispensing equipment.

Applications and Use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film, care should be taken with use on non-uniform surfaces and where a high level of squeezability is desired.

Automatic application: The robust film liner allows for consistent, snap free application on high speed lines.


Conversion and Printing

The modified acrylic based topcoating can be printed by conventional printing techniques including flexo, screen, offset, letterpress, silkscreen, gravure, and hot or cold foiling processes. UV, water-based and solvent-based inks can be used. The topcoat is designed for optimal ink adhesion. On-press corona treatment is not advised. The face material is suitable for Thermal Transfer printing. Exact inks, foils and ribbons should be specified by your ink/foil/ribbon supplier. The material has very good register properties especially when a high number of different colours are used.

AR107

Fasson®

PP50 TOP CLEAR S7000-rPET23



PP50 TOP CLEAR

S7000

rPET23

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

As the liner is transparent, the applicator must detect the print itself or registration marks must be provided on either face or liner. Press stability is good with stable, consistent register during conversion. Flat bed performance is good while solid and magnetic rotary dies need additional care. (Die bearers must be adjusted to the polyester liner). The PCR content gives a transparent light blue/grey shade to the liner. This does not affect the performance; performance is on par with conventional PET liners.

Compliance and Approvals

S7000 complies with European food regulation 1935/2004/EC, with the German Recommendation (BfR) XIV and FDA § 175.105. It also meets the demands of the limit values laid down in 10/2011/EU. In accordance with the requirements of relevant EU food regulations, the adhesive S7000 may safely stand in direct contact with dry and moist, such kind of fatty foodstuff which have a reduction factor of 4 according to EU Commission Regulation (No.) 10/2011. This is based on migration results from testing in olive oil as simulant. Furthermore, the seams (edges) of the label material may safely come into direct contact with all kinds of foodstuffs.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2021 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.