

Facestock

A satin white polypropylene with highly absorbent surface structure specifically designed for water-based inkjet printing with both dye- or pigment- based inks.

Basis Weight	72 g/m ²	ISO 536
Caliper	89 µm	ISO 534

Adhesive

A general purpose permanent, acrylic based adhesive.

Liner

BG40WH FSC, a supercalandered siliconized white glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	57 g/m ²	ISO 536
Caliper	51 µm	ISO 534

Laminate

Total Caliper	157 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	10 N/25mm	FTM 9 Glass
Peel Adhesion 90°	6 N/25mm	FTM 2 St.St.
Min. Application Temp.	5 °C	
Service Temperature	-20 °C to 80 °C	

Adhesive Performance

S692N is a clear permanent adhesive featuring excellent UV resistance and weatherability together with good adhesion performance, even on apolar substrates.

Applications and Use

The product is used in a variety of labelling applications, when the advantages of digital printing: short runs, last minute changes, personalised layouts and fast turn-round full colour printing are required. The product is a result of the emerging demand for short run colour print, both in business and at home. The face material is designed to give excellent density, print definition and vivid colours with photo ink. Quick drying and enhanced moisture resistance offer good handleability after printing.

Conversion and Printing

The material has been designed for water-based inkjet printing with dye- or pigment-based inks. Due to the nature of this printing technology, applications that require a high level of waterfastness may need overvarnishing to protect the print.

Compliance and Approvals

The adhesive S692N is suitable for contact with dry, moist and fatty foodstuffs with a reduction factor of 3 or higher in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.

Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AW405

Fasson®

WBIJ PP90 SATIN WHITE S692N-BG40WH FSC



WBIJ PP90 SATIN WHITE

S692N

BG40WH FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.